

Reclaimed Loblolly Pine



Reclaimed from a variety of industrial sources, our Loblolly Pine Flooring is sawn from softer species of the southern yellow pine family. Shortleaf pine, loblolly pine, and slash pine trees are incorporated into this flooring, producing a softer, more rustic aesthetic. Composed of quartersawn and flatsawn boards, this floor is perfect for low-traffic and character-driven areas. Vacation homes, country bedrooms, and summer cabins are common applications.

Ring density is highly variable, and antique heartwood content ranges greatly.

Standard Dimensions

2.5" - 11.5" wide planks (*wider w/ special order*)

2' to 12' lengths

3/4" thick, tongue-and-groove



Grain

Straight, with irregularities, figure, and variable heartwood content. Mixed flat and quartersawn. Some wider grain for variable ring density.

Color

Heartwood ranges from yellow to orange, with sapwood ranging from pale whitish to yellows. Mineral staining may occur, presenting shades and tones of gray.

Character

Knots, nail holes, mineral staining, plugged bolt holes, and checking.

Hardness & Stability

A medium soft and stable wood. 690lb_f on the Janka hardness scale. ~2.20 pounds per square foot.



Certifications

Qualifies for LEED MRc3, Materials Reuse credit. May qualify for LEED MRc5, Regional Materials credit.

Longleaf Lumber Inc. ~ 115 Fawcett Street, Cambridge, Massachusetts 02138

617.871.6611 | info@longleaflumber.com